

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 820 300 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
10.03.2004 Bulletin 2004/11

(51) Int Cl.7: **A61K 38/28, A61K 9/51,
A61K 47/48**

(21) Application number: 96909320.2

(86) International application number:
PCT/IE1996/000018

(22) Date of filing: 02.04.1996

(87) International publication number:
WO 1996/031231 (10.10.1996 Gazette 1996/45)

(54) **CONTROLLED RELEASE BIODEGRADABLE NANOPARTICLES CONTAINING INSULIN**
BIOLOGISCH ABBAUBARE NANOPARTIKEL MIT KONTROLLIERTER FREIGABE VON INSULIN
NANOPARTICULES BIODEGRADABLES A LIBERATION LENTE RENFERMANT DE L'INSULINE

(84) Designated Contracting States:
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**

(30) Priority: 04.04.1995 IE 950237

(43) Date of publication of application:
28.01.1998 Bulletin 1998/05

(73) Proprietor: **ELAN CORPORATION, Plc**
Dublin 2 (IE)

(72) Inventor: **RAMTOOLA, Zebunnissa**
Dublin 9 (IE)

(74) Representative: **Ryan, Anne Mary**
c/o Anne Ryan & Co.
60 Northumberland Road
Ballsbridge Dublin 4 (IE)

(56) References cited:
EP-A- 0 064 967 **WO-A-94/17789**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 820 300 B1

DescriptionTechnical Field

- 5 [0001] This invention relates to controlled release biodegradable nanoparticle formulations and, in particular, biodegradable polyalkylcyanoacrylate nanoparticles containing insulin or insulin analogues.

Background Art

- 10 [0002] Polyalkylcyanoacrylate nanoparticles have been studied as potential drug carriers for sustained release formulations, for drug targeting and for improving the bioavailability of peptides and proteins such as insulin, calcitonin and growth hormone releasing factor (Damgé, C. et al., *Diabetes*, 37:246(51) (1988); Lowe, P. et al., *J. Pharma. Pharmacol.*, 46:547-52 (1994); and Gautier, J. et al., *J. Controlled Release*, 20:67-78 (1992)). The short chain cyanoacrylate monomers, such as *n*-butyl, isobutyl and isohexylcyanoacrylate, are typically used because of their short degradation
15 times and low toxicities.

- [0003] Two methods are commonly employed for the preparation of these nanoparticles: the interfacial polymerisation method and the anionic polymerisation method. In the interfacial polymerisation method, the monomer and the drug are dissolved in an organic phase with polymerisation occurring at the organic-aqueous interface upon addition of the organic phase to an aqueous phase (Al Khouri, N. et al., *Int. J. Pharm.*, 28:125-32 (1986). This method produces
20 nanocapsules. In general, prior art peptide loaded nanoparticles have been produced by this technique (see, e.g., EP-A-0 608 207; EP-A-0 447 318; and FR-A-2,515,960).

- [0004] Anionic polymerisation occurs in aqueous media at low pH and is catalyzed by hydroxyl ions. In this method, the drug can be incorporated within the nanoparticle, adsorbed onto the nanoparticles or a combination of both depending on the time of addition of the drug to the polymerisation medium (Couvreur, P. et al., *J. Pharma. Pharmacol.*,
25 31:331-2 (1979)).

- [0005] Vidarabine-associated polyalkylcyanoacrylate nanoparticles, which result from vidarabine chemically interacting with the cyanoacrylic monomer during the polymerisation process, have been made using the anionic polymerisation method modified by the mandatory inclusion of dioctylsulfosuccinate in the aqueous media. However, formation of the polyalkylcyanoacrylate/vidarabine complex inactivated the biological activity of the vidarabine (Guise, V., et al.,
30 *Pharmaceutical Res.*, 7:736-41 (1990)).

- [0006] Administration of exogenous insulin can ameliorate metabolic abnormalities in type II diabetes by compensating for reduced endogenous insulin secretion, reducing excessive hepatic glucose production and stimulating glucose uptake. Additionally, non-substitutional insulin administration in non-insulin dependent diabetes is indicated where, without it, satisfactory compensation of diabetes is not achieved. Side effects possible from insulin therapy
35 include weight gain, hyperinsulinemia and hypoglycemia.

- [0007] Although single or multiple daily subcutaneous injections of insulin are the mainstay of insulin delivery techniques, several other methods of insulin delivery are now available or in development, including (a) continuous subcutaneous insulin infusion by a wearable infusion pump; (b) total or segmental transplantation of a pancreas; (c) transplantation of isolated islet cells; (d) implantation of a programmable insulin pump; (e) oral, nasal, rectal and transdermal mechanisms of insulin delivery; (f) administration of insulin analogues; (g) implantation of polymeric capsules which
40 give continuous or time-pulsed release of insulin; and (h) implantation of a biohybrid artificial pancreas which uses encapsulated islets. Despite these advances, the ideal delivery of insulin to patients has yet to be developed. For instance, subcutaneous and oral methods of insulin delivery do not currently mimic physiological insulin needs and transplantation requires risky immunosuppression.

- 45 [0008] Thus, there exists a need for improved insulin formulations, particularly controlled release bioactive oral formulations including those targeted to the small intestine and controlled release parenteral formulations to mimic physiological insulin needs.

Disclosure of Invention

- 50 [0009] This invention provides a controlled release pharmaceutical formulation, which comprises insulin entrapped in a biodegradable polyalkylcyanoacrylate polymer to form nanoparticles, wherein the insulin is complexed to the polyalkylcyanoacrylate.

[0010] As used herein, the term "insulin" refers to insulin and analogues of insulin having similar physical properties.

- 55 [0011] As used herein, the term "polyalkylcyanoacrylate" refers to poly(2-12 C (straight or branched chain) alkyl 2-cyanoacrylates. Preferred polyalkylcyanoacrylates include polymers formed from 4-6 C alkylcyanoacrylate monomers such as *n*-butylcyanoacrylate, isobutylcyanoacrylate and isohexylcyanoacrylate or mixtures thereof.

[0012] As used herein, the term "biodegradable" as applied to polyalkylcyanoacrylate polymers means polymers

which are degradable *in vivo* either enzymatically or non-enzymatically to produce biocompatible or non-toxic by-products which can be further metabolized or excreted *via* normal physiological pathways.

[0013] The biodegradable polyalkylcyanoacrylate polymer is suitably *n*-butylcyanoacrylate, isobutylcyanoacrylate or isohexylcyanoacrylate monomers or mixtures thereof.

5 [0014] Surprisingly, this invention discloses that at low pH and otherwise typical anionic polymerisation conditions, insulin complexes with polycyanoacrylate during the polymerisation step, forming polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles. At higher pH, the insulin does not complex with the polymer but, rather, is incorporated into nanoparticles as free insulin. Further surprisingly, the polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles are capable of releasing bioactive insulin *in vivo*. The rate of insulin release from these polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles is slower than that from corresponding free insulin-loaded polyalkylcyanoacrylate nanoparticles. At an intermediate pH, the nanoparticles can be a natural mixture of free and complexed insulin.

10 [0015] Thus, this invention provides oral and parenteral formulations containing polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles that are capable of releasing pharmaceutically effective amounts of bioactive insulin in a controlled fashion to satisfy physiological insulin needs when orally or parenterally administered to a subject, particularly a human. Further, the controlled release nature of these formulations makes possible the targeting of insulin to the small intestine when administered orally, which enhances the bioavailability of the insulin. Optionally, these oral and parenteral formulations may comprise a mixture of polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles and free insulin-loaded polyalkylcyanoacrylate nanoparticles.

15 [0016] The biodegradable nanoparticles preferably contain 5% to 30% w/v of insulin to monomer content, more especially 15-25% w/v insulin.

20 [0017] The size of the biodegradable nanoparticles suitably is 50-900 nm, preferably 100-400 nm.

[0018] The polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles in accordance with the invention and, optionally, free insulin-loaded polyalkylcyanoacrylate nanoparticles, if present, are suitably incorporated into oral dosage forms, such as capsules, tablets, powders including powders capable of effervescing upon addition of water, or suspensions. Additionally, an enteric coating can be applied to the polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles and, optionally, free insulin-loaded polyalkylcyanoacrylate nanoparticles, if present, to protect the formulation while it passes through the stomach to further target release of insulin to the small intestine. Alternatively, the nanoparticles can be administered parenterally to release insulin to mimic physiological insulin needs.

25 [0019] Thus, for convenient and effective oral administration, pharmaceutically effective amounts of the nanoparticles of this invention can be tableted with one or more excipient(s), encased in capsules such as gel capsules, formulated with ingredients which upon addition of water, provide an effervescent solution, and suspended in a liquid solution and the like. The nanoparticles can be suspended in a saline solution or the like for parenteral administration.

[0020] When the nanoparticles are tableted, the tablets optionally comprise an enteric coating on the tablet to target release of insulin to the small intestine when administered orally.

30 [0021] It will be appreciated that the pharmaceutical formulations in accordance with the invention can be used *inter alia* to provide exogenous insulin to patients with type II diabetes or to treat non-insulin dependent diabetes. Suitably, the formulations of this invention are administered to humans at an insulin dose, which varies from individual to individual, such that the blood glucose levels are adjusted to stay within normal ranges. The oral formulations preferably are designed as 4-times daily products while the parenteral formulations, which typically have ≥ 100 IU of bioavailable insulin per ml, can be administered once or twice daily up to once weekly.

Brief Description of Drawings

45 [0022]

Figure 1 shows the mechanistic pathway for the anionic polymerisation method of forming polyalkylcyanoacrylate nanoparticles;

50 Figure 2 shows blood glucose levels over six hours expressed as a percentage of baseline values for four groups of male Wistar rats: Control (n=4; untreated rats); insulin solution (n=4; solution containing 2.5 IU insulin administered by IM injection to each rat at time 0); pH = 2 (n=4; aqueous suspension of insulin-loaded polyalkylcyanoacrylate nanoparticles (16 IU) produced at pH = 2 administered by IM injection to each rat at time 0); and pH = 4.8 (n=3; aqueous suspension of insulin-loaded polyalkylcyanoacrylate nanoparticles (16 IU) produced at pH 4.8 administered by IM injection to each rat at time 0); and

55 Figure 3 shows blood glucose levels over 4 hours expressed as a percentage of baseline values for two groups of male Wistar rats: Control (n=8; untreated rats) and Study (n=5; aqueous suspension of insulin-loaded polyalkylcyanoacrylate nanoparticles (204 IU) produced at pH = 2 administered orally to each rat at time 0).

Modes for Carrying Out the Invention

[0023] In the following Examples, *n*-butylcyanoacrylate was donated by Loctite Ltd. (Ireland). Isobutylcyanoacrylate, Dextran 10, 40 and 70 and insulin (bovine) were obtained from Sigma. Surface morphology of the nanoparticles produced was studied by scanning electron microscopy (SEM) (Leica Cambridge S360). Drug loading was monitored by the method of residuals using UV spectroscopy and by gradient HPLC analysis according to USP XXII. Male Wistar rats were used in the *in vivo* studies and blood glucose levels were monitored by an Ames™ Glucostix system.

Example 1Effect of Choice of Monomer upon Nanoparticle Characteristics

[0024] Biodegradable polyalkylcyanoacrylate nanoparticles were produced from *n*- and isobutylcyanoacrylate using the anionic polymerisation method under standard conditions. For instance, for 20% starting drug loading, 100 mg of insulin was dissolved in 49.5 ml of a 0.01M HCl solution containing 0.5% Dextran 70 (as a stabiliser) prior to addition of the monomer. After adding the monomer, e.g., 0.5 ml isobutylcyanoacrylate, the solution was stirred for 4 hours, filtered or centrifuged and dried overnight. No difference in particle morphology between particles formed from *n*- or isobutylcyanoacrylate was observed under these conditions. The surface of particles produced was smooth and free of drug crystals and the particles were 100 nm - 400 nm in diameter. For a starting loading of 20% w/w, insulin loading values of 17.82% for *n*-butylcyanoacrylate and 17.97% for isobutylcyanoacrylate were obtained. Thus, the formation of insulin-loaded nanoparticles was not influenced by the choice of these monomers.

Example 2Effect of Stabiliser Molecular Weight and Concentration upon Nanoparticle Characteristics

[0025] Nanoparticles were produced using the method outlined in Example 1 to study the effect of varying the molecular weight of the stabiliser Dextran (using Dextran 10, Dextran 40 and Dextran 70; $M_w = 10,000, 40,000$ and $70,000$, respectively) at a concentration of 0.5% w/v on nanoparticle formation. Additionally, using Dextran 70, the concentration of the Dextran was also varied from 0.05 to 1% w/v. As shown in Table 1, no difference in nanoparticle size and morphology or in insulin entrapment efficiency was observed when either the molecular weight or concentration of the Dextran used was varied. This result for insulin-loaded polyalkylcyanoacrylate nanoparticles is contrary to that reported for empty polyalkylcyanoacrylate nanoparticles (Douglas, S. et al., *J. Colloid Interface Science*, **103**:154-63 (1985).

TABLE 1:

Influence of Molecular Weight and Concentration of Dextran on Insulin Loading of Nanoparticles		
Dextran Type	Dextran Concentration (% w/v)	Insulin Loading (% w/w)
Dextran 10	0.50	18.00
Dextran 40	0.50	16.90
Dextran 70	0.05	18.04
Dextran 70	0.10	18.53
Dextran 70	0.25	18.25
Dextran 70	0.50	19.07
Dextran 70	1.00	18.18

Example 3The Effect of Polymerisation Medium pH upon Nanoparticle Characteristics

[0026] Insulin-loaded *n*-butylcyanoacrylate nanoparticles were produced using the method outlined in Example 1 to study the effect of varying the pH of the polymerisation medium from 1 to 4.8 on nanoparticle formation. As the pH of the polymerisation medium was increased above 3, defined, distinct particles were produced having smooth, drug-crystal free surfaces. However, below a pH of 3, formation of distinct nanoparticles appeared to be limited, showing only small quantities of well-formed nanoparticles. At this low pH, the formation of particles occurs quickly, resulting in

the majority of nanoparticles not being well formed.

[0027] Additional experimentation shows that a white frothy precipitate results when insulin, at 10% and 20% w/v of monomer content, is first dissolved in a 0.1M HCl solution containing 0.5% w/v Dextran 70 to which 0.25 ml isobutylcyanoacrylate monomer is added. The precipitate can be collected by filtration and dried to give a fine white powder (100-400 nm). This reaction does not occur in the absence of insulin in the HCl solution or if the insulin is added after the cyanoacrylate monomer.

[0028] Without being bound by any theoretical explanation, it is suggested that these observations may be explained, with hindsight, by reference to the mechanism by which anionic polymerisation occurs and the physicochemical properties of insulin. As shown in Figure 1, the hydroxyl ions present in the aqueous polymerisation medium initiate polymerisation. Because insulin is a peptide with an isoelectric point of 5.3, at a pH below 5.3 it is positively charged, while at a pH greater than 5.3 insulin is capable of being negatively charged. At low pH ($\text{pH} \leq 2$), the insulin molecule has a net charge of +6 and can complex with the negatively charged cyanoacrylate short chains resulting in a termination of the polymerisation process. As the pH of the polymerisation medium is increased to 5, the net charge on insulin approximates zero and, therefore, complexation with the cyanoacrylate short chains is unlikely. At that pH, well formed insulin-loaded nanoparticles are produced.

[0029] HPLC analysis of insulin content of the nanoparticles produced at pH 2 yielded no insulin peaks at the expected insulin retention time. However, UV analysis (by the method of residuals) indicated $\geq 80\%$ drug entrapment. HPLC analysis of nanoparticles produced at pH 4.8 showed the presence of insulin at the expected retention time of 19 minutes. These observations support the conclusion that, at low pH, insulin is complexed with the polymer and is not being eluted at the expected retention time for free insulin whereas at pH 4.8, free insulin is incorporated in the nanoparticles and is eluted at the expected retention time.

[0030] To support this conclusion, the formation of empty nanoparticles within the same pH range was investigated in order to establish if the presence of insulin inhibits nanoparticle formation at low pH. Nanoparticles were produced at pH 2, 3 and 4 under the same conditions as those employed for the insulin-loaded nanoparticles. In all cases, the nanoparticles produced were smooth, spherical and uniform in size. Thus, at low pH, the presence of insulin in the polymerisation medium interferes with nanoparticle formation.

Example 4

Intramuscular Administration of Insulin-loaded Nanoparticles to Rats

[0031] The bioactivity and release properties of the insulin-loaded *n*-butylcyanoacrylate nanoparticles produced according to Example 3 were examined by intramuscular (IM) administration to male Wistar rats. Insulin-loaded nanoparticles produced at pH 2 (16 IU) and pH 4.8 (16 IU) were administered in aqueous suspension by IM injection to two groups of rats and blood glucose levels were monitored over a six hour period. Pure insulin solution (2.5 IU) was administered by IM injection to a third group of rats to provide a comparison between delivery via the nanoparticulate formulations and unencapsulated insulin. The blood glucose levels of untreated rats (controls) were also monitored over the same time period.

[0032] Figure 2 shows the blood glucose levels for the pH 2, pH 4.8, control and untreated groups expressed as a percentage of baseline values. Blood glucose levels in the untreated group were within 87.6 to 108.9% of the baseline value in the study period. Administration of the nanoparticles resulted in a steady reduction in blood glucose levels to 20% of the baseline value, indicating that the insulin from both types of nanoparticles (complexed at pH 2; free insulin at pH 4.8) is bioactive and is released in a controlled, sustained fashion. The blood glucose reduction was faster for nanoparticles produced at pH 4.8 than for those produced at pH 2, presumably due to the faster release of free insulin from the pH 4.8 formulation as opposed to the slower release of insulin complexed with polyalkylcyanoacrylate in the pH 2 formulation.

Example 5

Oral Administration of Insulin-loaded Nanoparticles to Rats

[0033] The bioactivity and release properties of the insulin-loaded *n*-butylcyanoacrylate nanoparticles produced according to Example 3 were examined by oral administration to male Wistar rats. Insulin-loaded nanoparticles produced at pH 2 were administered orally in an aqueous suspension to a group of rats and blood glucose levels were monitored over a four hour period. The dose administered *per rat* was 204 IU of insulin. The blood glucose levels of untreated rats were also monitored over the same time period.

[0034] Figure 3 shows the blood glucose levels for these two groups expressed as a percentage of baseline values. Blood glucose levels in untreated rats were between 85 and 100% of the baseline value during the study period. In

the treated rats, a reduction in blood glucose levels to 35% of the baseline value was observed over a four hour period giving an oral bioavailability of $\geq 7\%$ for these insulin-loaded nanoparticles. These results indicate that the insulin from nanoparticles produced at pH 2 (complexed to the polyalkylcyanoacrylate) is bioactive and is released in a controlled, sustained fashion.

5

Claims

1. A controlled release pharmaceutical formulation, which comprises insulin entrapped in a biodegradable polyalkylcyanoacrylate polymer to form nanoparticles, wherein the insulin is complexed to the polyalkylcyanoacrylate.
2. A controlled release pharmaceutical formulation according to Claim 1, wherein the polyalkylcyanoacrylate is formed from n-butylcyanoacrylate, isobutylcyanoacrylate or isohexylcyanoacrylate monomers or mixtures thereof.
3. A controlled release pharmaceutical formulation according to any preceding claim, wherein the insulin loading ranges from about 5% to 30% w/v of monomer content.
4. A controlled release pharmaceutical formulation according to any preceding claim, further comprising free insulin-loaded polyalkylcyanoacrylate nanoparticles to form a mixture of polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles and free insulin-loaded polyalkylcyanoacrylate nanoparticles.
5. A controlled release pharmaceutical formulation according to any preceding claim, further comprising an enteric coating on the polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles to target release of insulin to the small intestine when administered orally.
6. A controlled release pharmaceutical formulation according to Claim 4 or 5, further comprising an enteric coating on the free insulin-loaded polyalkylcyanoacrylate nanoparticles to target release of insulin to the small intestine when administered orally.
7. A controlled release pharmaceutical formulation according to any preceding claim, where the formulation is formulated as capsules, tablets, powders, powders capable of effervescing upon addition of water, or suspensions.
8. A controlled release pharmaceutical formulation according to Claim 7, where the formulation is formulated as tablets and further comprising an enteric coating on the tablet to target release of insulin to the small intestine when administered orally.
9. A controlled release pharmaceutical formulation according to any preceding claim and adapted for oral administration.
10. A controlled release pharmaceutical formulation according to any of Claims 1-4 and 7 and adapted for parenteral administration.

25

30

35

40

Patentansprüche

45

50

55

1. Arzneizubereitung mit kontrollierter Freigabe, umfassend in ein biologisch abbaubares Polyalkylcyanoacrylat-Polymer eingeschlossenes Insulin zur Bildung von Nanopartikeln, wobei das Insulin am Polyalkylcyanoacrylat komplexiert ist.
2. Arzneizubereitung mit kontrollierter Freigabe nach Anspruch 1, wobei das Polyalkylcyanoacrylat aus n-Butylcyanoacrylat-, Isobutylcyanoacrylat- oder Isohexylcyanoacrylat-Monomeren oder Mischungen davon gebildet ist.
3. Arzneizubereitung mit kontrollierter Freigabe nach einem der vorhergehenden Ansprüche, wobei die Insulinbeladung zwischen ungefähr 5 % bis 30 % w/v des Monomerinhalts liegt.
4. Arzneizubereitung mit kontrollierter Freigabe nach einem der vorhergehenden Ansprüche, umfassend ferner freie insulinbeladene Polyalkylcyanoacrylat-Nanopartikel zur Bildung einer Mischung von polyalkylcyanoacrylat-komplexierten insulinbeladenen Nanopartikeln und freien insulinbeladenen Polyalkylcyanoacrylat-Nanopartikeln.

5. Arzneizubereitung mit kontrollierter Freigabe nach einem der vorhergehenden Ansprüche, umfassend ferner eine darmlösliche Beschichtung der polyalkylcyanoacrylat-komplexierten insulinbeladenen Nanopartikel zur gezielten Insulinfreigabe im Dünndarm bei oraler Verabreichung.
- 5 6. Arzneizubereitung mit kontrollierter Freigabe nach Anspruch 4 oder 5, umfassend ferner eine darmlösliche Beschichtung der freien insulinbeladenen Polyalkylcyanoacrylat-Nanopartikel zur gezielten Insulinfreigabe im Dünndarm bei oraler Verabreichung.
- 10 7. Arzneizubereitung mit kontrollierter Freigabe nach einem der vorhergehenden Ansprüche, wobei die Zubereitung in Form von Kapseln, Tabletten, Pulvern, Pulvern, die bei Wasserzugabe sprudeln können, oder Suspensionen zubereitet ist.
- 15 8. Arzneizubereitung mit kontrollierter Freigabe nach Anspruch 7, wobei die Zubereitung in Form von Tabletten zubereitet ist und ferner eine darmlösliche Beschichtung auf der Tablette zur gezielten Insulinfreigabe im Dünndarm bei oraler Verabreichung umfasst.
9. Arzneizubereitung mit kontrollierter Freigabe nach einem der vorhergehenden Ansprüche, die einer oralen Verabreichung angepasst ist.
- 20 10. Arzneizubereitung mit kontrollierter Freigabe nach einem der Ansprüche 1-4 und 7, die einer parenteralen Verabreichung angepasst ist.

Revendications

- 25 1. Formulation pharmaceutique à libération contrôlée, qui comprend de l'insuline piégée dans un polymère de poly(cyanoacrylate d'alkyle) biodégradable pour former des nanoparticules, dans laquelle l'insuline est complexée au poly(cyanoacrylate d'alkyle).
- 30 2. Formulation pharmaceutique à libération contrôlée selon la revendication 1, dans laquelle le poly(cyanoacrylate d'alkyle) est formé de monomères de cyanoacrylate de n-butyle, de cyanoacrylate d'isobutyle ou de cyanoacrylate d'isohexyle ou de mélanges de ceux-ci.
- 35 3. Formulation pharmaceutique à libération contrôlée selon l'une quelconque des revendications précédentes, dans laquelle la charge d'insuline est comprise entre environ 5% et 30% p/v de la teneur en monomère.
- 40 4. Formulation pharmaceutique à libération contrôlée selon l'une quelconque des revendications précédentes, comprenant de plus des nanoparticules de poly(cyanoacrylate d'alkyle) chargées d'insuline libre pour former un mélange de nanoparticules chargées d'insuline complexée par le poly(cyanoacrylate d'alkyle) et de nanoparticules de poly(cyanoacrylate d'alkyle) chargées d'insuline libre.
- 45 5. Formulation pharmaceutique à libération contrôlée selon l'une quelconque des revendications précédentes, comprenant de plus un enrobage gastrorésistant sur les nanoparticules chargées d'insuline complexée par le poly(cyanoacrylate d'alkyle) pour cibler la libération d'insuline au niveau de l'intestin grêle quand elle est administrée par voie orale.
- 50 6. Formulation pharmaceutique à libération contrôlée selon la revendication 4 ou 5, comprenant de plus un enrobage entérique sur les nanoparticules de poly(cyanoacrylate d'alkyle) chargées d'insuline libre pour cibler la libération d'insuline au niveau de l'intestin grêle quand elle est administrée par voie orale.
7. Formulation pharmaceutique à libération contrôlée selon l'une quelconque des revendications précédentes, où la formulation est formulée en gélules, comprimés, en poudres, en poudres pouvant être effervescentes après addition d'eau, ou en suspensions.
- 55 8. Formulation pharmaceutique à libération contrôlée selon la revendication 7, où la formulation est formulée en comprimés et comprenant de plus un enrobage entérique sur le comprimé pour cibler la libération d'insuline au niveau de l'intestin grêle quand elle est administrée par voie orale.

EP 0 820 300 B1

9. Formulation pharmaceutique à libération contrôlée selon l'une quelconque des revendications précédentes et adaptée pour une administration par voie orale.
10. Formulation pharmaceutique à libération contrôlée selon l'une quelconque des revendications 1 à 4 et 7 et adaptée pour une administration parentérale.

5

10

15

20

25

30

35


40

45

50

55

Figure 1



R = 2-12C alkyl such as butyl, isobutyl, isohexyl.

Figure 2




Figure 3.

